

EN-

007-0226

NAME:

Engineering

REV:

Α

Engineering Note

SUBJECT: CICOIL FLEXX-SIL RUBBER OUTGASSING PERFORMANCE

CICOIL outgassed cables meet the following outgassing requirements:

DETAILS

Certified to: TML (Total Mass Loss)	≤1.00%
CVCM (Collected Volatile Condensable Materials)	≤0.10%
Vacuum bake (PSI)	≤10 ⁻⁶ torr
Vacuum bake (Temp)	+160ºC
Vacuum Duration (h)	.48 hours

OTHER RATINGS:

NASA Outgassing sp	pecification	Spec 1124
Standard Test Metho	nd for TML and CVCM	ASTM F595-93

NOTES

- 1. Outgassing certificates available upon request.
- 2. Additional outgassing fee may apply, contact CICOIL for details.

Please contact CICOIL for more information.

